



BERGER **Protecton** PROTECTIVE COATINGS

Epilux 84 High Gloss CR Enamel

USES

Recommended for application in refineries, petrochemicals, heavy chemicals, fertilizers and pharmaceutical industries. Also suitable for concrete which is subjected to product splashes and spills.

SCOPE

A high performance epoxy coating unaffected by a broad spectrum of corrosive chemical and solvent exposure. It is specifically meant for protection against fumes, dust, splash and spillage.

PRODUCT DATA

Type : Two Pack, cured with Amine Adduct

Composition : Catalysed epoxy resin, suitably pigmented

Mixing Ratio : Base : Catalyst – 3 : 1 by volume

Pot Life : 4–6 hours

Application : Brush, Conventional or Airless Spray

Recommended DFT : 30–35 microns per coat

Corresponding WFT : 70–81 microns per coat

Theoretical Spreading Rate : 12.3–14.3 Sq. Mtr./Ltr.

Drying Time :

TOUCH : 2–3 hours
HANDLE : 6–8 hours
HARD : Overnight

Curing Time : 6–7 days

Overcoating Interval :

MIN : Overnight
MAX : 5 days

Flash Point : Above 22° C

Colour : Assorted shades

Packing : 20 Ltrs.

Thinner/Cleaner : Thinner 844

Finish : High Gloss

Storage Life : Upto twelve months as long as the sealed containers are kept under cover in a dry place under normal temperature conditions.

RESISTANCE GUIDE

Chemical Resistance :

EXPOSURES	SPLASH & SPILLAGE	MILD FUMES / OUTDOOR RESISTANCE
Acids	Good	Very Good
Alkalis	Very Good	Excellent
Solvents	Very Good	Excellent
Salt	Very Good	Very Good
Water	Very Good	Very Good

Temperature Resistance :

Continuous : 93° C
Intermittent : 120° C

Weatherability : Excellent in combination with a suitable primer

Flexibility : Excellent

Abrasion Resistance : Very Good

SURFACE PREPARATION

Steel : Remove grease, oil and other contaminants preferably by using Bison Degreasing Solvent. Blast clean to a minimum of Sa 2 1/2 Swedish Standard SIS 05 5900 with a surface profile not exceeding 35 – 40 microns.

If blasting is not practical, make full use of mechanical tools along with manual chipping and wire brushing to remove loose rust and scale to St. 2 Swedish Standard SIS 05 5900. Excessive burnishing of steel is to be avoided. Thoroughly dust down all surfaces. Best results can be achieved if the manually cleaned surface is primed with Protectomastic – Self Priming Surface Tolerant Coating. The surface should be clean and dry before application of appropriate coat.

Concrete : **NEW CONCRETE** : Ensure that the concrete is cured for a minimum of 3 months. Surface is to be made rough and free from laitance and other contaminants by sand sweeping. **OLD CONCRETE** : Remove all salt deposits from the surface by water jet washing. Light sand blast the surface to remove all loosely bound coatings and roughening of firmly adhering coatings to ensure anchorage with recommended system. Ensure all dust/other particles are fully removed by suction or air blast and the surface is fully clean and dry before application of paint. In non-critical areas where blasting is not possible, water jet washing and hard wire brushing are minimum requisites.

APPLICATION

Stir the base thoroughly and then mix three parts base and one part catalyst by volume to uniform consistency. Allow the mixture to mature for 30 minutes and stir again before application and during use.

Brush : Apply without thinning. However, if required during application add maximum upto 5% Thinner 844.

Conventional Spray : Add upto 10% Thinner 844 depending on conditions. Use any standard equipment at an atomising pressure of 3.5–4.2 Kg/cm².

Airless Spray : Apply preferably without thinning. However, upto 5% Thinner 844 may be added if absolutely essential depending on conditions. Use any standard equipment having pump ratio 30 : 1. Tip size 0.33–0.38 mm. Tip pressure 110–140 Kg/cm².

TYPICAL PAINTING SPECIFICATIONS

Surface	1st Coat	2nd Coat	3rd Coat	4th Coat
Steel	Epilux 4 Z/R Primer or Epilux 610 Primer or Epilux 13 Primer	Epilux 4 Z/R Primer or Epilux 610 Primer or Epilux 13 Primer	Epilux 84 HG CR Enl.	Epilux 84 HG CR Enl.
-do-	Protectomastic	Epilux 4 MIO	-do-	-do-
Concrete or Plastered Surfaces	Epilux 4 Clear Lacquer	Epilux 84 HG CR Enl.	-do-	
Galvanised Iron & Aluminium	Degrease and abrade the surface. Apply a coat of Bison Wash Primer followed by any of the above systems mentioned above excluding the primer coats.			

Notes :

1. Use off the mixed paint within the stipulated pot life period.
2. Do not apply when temperature falls below 10° C or rises above 50° C and when relative humidity rises above 90%. Do not apply during rain, fog or mist.
3. Brushes & spray equipment should be cleaned with Thinner 844, otherwise equipment is liable to be damaged.

DISCLAIMER

The information contained within this Data Sheet is based on information believed to be reliable at the time of its preparation. The Company will not be liable for loss or damage howsoever caused including liability for negligence, which may be suffered by the user of the data contained herein. It is the users' responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of results is implied since conditions of use are beyond our control.

DATA SHEET No. : 048
Issue Date : Mar. 04

BERGER PAINTS INDIA LIMITED

Berger House, 129 Park Street, Kolkata 700017 **Phone** : (033) 2229 9724 (5 lines) / 249 9754 (4 lines) **Fax** : 91-33-2249 9729 / 2249 9009
Email : **NORTH** : bpil_okh@mantraonline.com **SOUTH** : bpil_ch2@sify.com **EAST** : bpil_cl1@vsnl.net **WEST** : bpil_vsh@vsnl.net